

Technical data sheet

ARTICRYL-Naturmatt CM3001-0005

Product description

ARTICRYL-Naturmatt is a 2-component polyurethane lacquer system based on special resins included UV-filters. ARTICRYL-Naturmatt retains the natural character of untreated wood, delays the normal wood discolouration .

In open-pored paint systems there is a risk that liquids (for example oil, coloring liquids) from penetrating into the pores and wets them. As a result, discoloration may occur in the pore region.

Product data

Gloss:	4-6	
Shade:	deep matt	
Non-volatile contents:	15,9 %	
Density:	0,921 g/ml	
Viscosity:	28-30 sec	DIN 4 mm / 20° C
Decree combustible liquids:	AI	
Frost sensitive:		
Storing:	12 months	(unopened 15-25° C)

Mixing / Application

Application methods: Spraying - AIRMIX (Air assisted), Airless

Hardener	Amount*	Thinner	Viscosity DIN 4	Application amount	Pot-life
06111 (SV3000)	10	0988 (ST3000)	18-20 sec	80-120 g/m ²	24 hours

* To 100 parts paint by volume

Stir well before use!

Drying / Curing

Method	Drying conditions	Drying time	Notes:
Air drying	20° C	2 hours 24 hours	for sanding for stacking
Forced drying	By increased temperatures, all kind of drying requires good ventilation and circulation		

Safety instructions

General Information

According to German legislation we provide information regarding dangerous materials. The Safety Data Sheet contains facts about the components, which present the dangerous characteristics. The Safety Data Sheet will be sent on request. All values and recommendations above are to be considered as guidance only. Many factors beyond our control may have an influence on the coating result. Should a problem arise, please contact us and we will advise accordingly. We reserve the right to alter the above specifications.

ARTI is a brand of **SHERWIN-WILLIAMS**

Sherwin-Williams Deutschland GmbH Paul-Gerhardt-Str.31 D-42389 Wuppertal | Postfach 22 01 02 D-42371 Wuppertal |

Fon +49 202 57 47 0 | Fax+ +49 202 55 51 82 | office@arti. de | www.arti.de | Geschäftsführer Andy Schumacher |

UST-IdNr. DE814804204 | Steuer-Nr. 131 / 5902 / 0970 | Rechtsform GmbH | Sitz Wuppertal |Eingetragen HRB 20277 Amtsgericht Wuppertal |

Bankverbindung JPMorgan AG | Konto-Nr.: 6161510513 (BLZ 501 108 00|IBAN: DE52501108006161510513 | SWIFT BIC: CHASDEFX

