

# Technical Data Sheet

EM4041-00..

## Description

**Waterborne clear one-component top coat/ sealer for interior**

## Main use

Parquet.

## Properties

**Drying fastness: very good**  
**Elasticity: very good**  
**Chemical-physical resistance: very good**  
**Surface hardness: very good**  
**Smoothness to the touch: Very good**

## Technical data

<b>Viscosity</b>	40 (± 3)	s Din Cup 4 at 20°C
<b>Density</b>	1,04 (± 0,03)	kg/l
<b>Gloss level</b>	5, 10, 20, 30, 50, 80	Gardner 60°
<b>Flashpoint</b>	non infiammabile/not flammable	Method: closed cup
<b>Solid content (weight)</b>	31 (± 2)	% by weight
<b>Storage stability</b>	15 months at 5°C ÷ 35°C	

## Product preparation

Application	Manual spraying	Brush	Roller
Thinner			H2O 10
	% by weight		
<b>Working temperature</b>	>15°C	coating, objects, air, substrate	
<b>Number of coats</b>	max 3		
<b>Interval between coats</b>	2 h		
<b>Suggested weight</b>	60-100 gr/m2		

## Technical information

### Drying time

<b>Dust free</b>	15-20 min
<b>Touch dry</b>	30-40 min
<b>Dry for sanding</b>	2 h
<b>Overcoating</b>	2 h
<b>Foot traffic</b>	24 h

### Sherwin-Williams Italy S.r.l. - con unico socio

Sede legale ed Amministrativa: Via del Fiffo, 12 - 40065 Pianoro (BO) - Italia - C.P. 18 - tel. +39 051 770 511 - fax +39 051 777 737 - servizioclienti@sherwin.com  
 Cod. Fisc. E Reg. Impr. Bo 08866930152 - P. IVA: IT 00494251200 - Cap. Soc. Euro 2.626.182 I.V. - Codice Mecc. Bo 014531  
 Società soggetta a direzione e coordinamento di: The Sherwin-Williams Company, USA

# Technical Data Sheet

EM4041-00..

## Special instructions

Stir thoroughly before using

The product is sensitive to cold: keep it at temperatures from 5°C up.

## FOR INDUSTRIAL USE ONLY

N.B.: Data provided on this technical data sheet correspond to our best knowledge and experience. we assure consistency on the chemical-physical characteristics of our products, within the tolerance limits specified in our technical data sheets. Responsibility of final result of product application is fully up to the users, who shall make sure that the product corresponds to their own needs with regard to application system, to substrates used as well as to working conditions.

Warning: actual viscosity of some pigmented and/or thixotropic products may differ from the viscosity shown on the technical data sheet. Differences are to be regarded as acceptable if within 30% maximum.

Date: 09/2016

### Sherwin-Williams Italy S.r.l. - con unico socio

Sede legale ed Amministrativa: Via del Fiffo, 12 - 40065 Pianoro (BO) - Italia - C.P. 18 - tel. +39 051 770 511 - fax +39 051 777 737 - servizioclienti@sherwin.com

Cod. Fisc. E Reg. Impr. Bo 08866930152 - P. IVA: IT 00494251200 - Cap. Soc. Euro 2.626.182 I.V. - Codice Mecc. Bo 014531

Società soggetta a direzione e coordinamento di: The Sherwin-Williams Company, USA