

Description

Solventborne White Two-pack Deep matt with special smoothness to the touch Top coat high performance

Main use

Furniture.

Properties

Smoothness to the touch: Excellent  
Scratching resistant: Excellent  
Non-yellowing power: Excellent  
Chemical-physical resistance: Excellent

Technical data

Viscosity	35 ± 5	s D6 20°C
Density	1,050 ± 0,030	kg/l
Gloss level	2-3	Gardner 60°
Flashpoint	16	Method: closed cup
Solid content (weight)	36 ± 1	% by weight
Storage stability	12 months at 25 °C	

Product preparation

Application	Airmix		Robot	
	% by weight		% by weight	
Catalyst	SV4310	25	SV4310	25
Thinner	TT4209	15-30	TT4720	10-20
Mix. Viscosity	20-25 s D4		20-25 s D4	
Number of coats	1			
Suggested weight	100-150 g/m2			

Technical information

	Drying time
Touch dry	3-4 h
Dry for stacking	24-48
Complete dry time	80-100

Sherwin-Williams Italy S.r.l. - con unico socio

Sede legale ed Amministrativa: Via del Fiffo, 12 - 40065 Pianoro (BO) - Italia - C.P. 18 - tel. +39 051 770 511 - fax +39 051 777 737 - servizioclienti@sherwin.com  
Cod. Fisc. E Reg. Impr. Bo 08866930152 - P. IVA: IT 00494251200 - Cap. Soc. Euro 2.626.182 I.V. - Codice Mecc. Bo 014531  
Società soggetta a direzione e coordinamento di: The Sherwin-Williams Company, USA

**Special instructions**

It can be pigmented with the traditional solvent-based alkyd pastes TZ4109-XXXX at a maximum % of 2.5%

It is always advisable to carry out a preventive test to verify the suitability of the cycle to be used

For industrial applications it is advisable to use the thinner TT4720 to obtain maximum homogeneity.

**FOR INDUSTRIAL USE ONLY**

N.B.: Data provided on this technical data sheet correspond to our best knowledge and experience. we assure consistency on the chemical-physical characteristics of our products, within the tolerance limits specified in our technical data sheets. Responsibility of final result of product application is fully up to the users, who shall make sure that the product corresponds to their own needs with regard to application system, to substrates used as well as to working conditions.

Warning: actual viscosity of some pigmented and/or thixotropic products may differ from the viscosity shown on the technical data sheet. Differences are to be regarded as acceptable if within 30% maximum.

Date: 03/2023

**Sherwin-Williams Italy S.r.l. - con unico socio**

Sede legale ed Amministrativa: Via del Fiffo, 12 - 40065 Pianoro (BO) - Italia - C.P. 18 - tel. +39 051 770 511 - fax +39 051 777 737 - servizioclienti@sherwin.com

Cod. Fisc. E Reg. Impr. Bo 08866930152 - P. IVA: IT 00494251200 - Cap. Soc. Euro 2.626.182 I.V. - Codice Mecc. Bo 014531

Società soggetta a direzione e coordinamento di: The Sherwin-Williams Company, USA